



Never compromise on quality!

PC800 PIPESEAL

Rigid PVC Pipe Weld Cement

Description

A pipe weld cement specially developed for bonding rigid PVC or ABS.

Complies with the requirements of BS Specification 4346-Part 3: 1982. It also meets the requirements of the Water Byelaws Scheme BS6920:1996 for cold water use.

Uses

PC800 PIPESEAL is used for jointing rigid PVC water pipes. It is also suitable for many applications in the construction industry such as jointing PVC rainwater and drainage systems.

Preliminary Check

Before jointing, the pipe fittings should be checked for position and alignment, both being marked to ensure assembly in the correct position.

Preparation

1. Pipe ends should be smooth and square.
2. Thoroughly clean the pipe end and socket with a cleaning fluid.

Making The Joint

1. Apply a uniform coat of cement to both pipe end and socket using the applicator brush. If the preliminary check indicated a tight fit, immediately insert the pipe into the socket with a slight twisting action.
2. If the preliminary check indicated a loose fit, allow the first coat of cement to dry for 5 minutes. Apply a second coat once dry to both surfaces and assemble the joints as above.

Storage Conditions

Store in cool, dry conditions in tightly sealed container. Store between a temperature of +5°C and +20°C.

Shelf Life

18 months in original, unopened containers.

Disposal of Containers

Do not leave empty containers where residue could be harmful to children, animals or the environment. Replace lids and remove any containers to a central disposal point in accordance with local regulations. This material and its container must be disposed of as hazardous waste.

Health & Safety

- ◆ Highly flammable.
- ◆ Irritating to eyes and respiratory system.
- ◆ Keep container in a well ventilated place.
- ◆ Keep away from sources of ignition - no smoking.
- ◆ Avoid contact with eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- ◆ Use only in well ventilated areas.
- ◆ Keep out of reach of children.

Always follow the manufacturer's recommendations when using this product. It is the users responsibility to determine suitability. Safety data sheet available on request for professional user.

Specification Summary

Flammability	Highly flammable
Total Solids	22+/- 1%
Typical Specific Gravity	0.97
Viscosity	39,000+/- 2000 cps
Flashpoint	-14°C

Container Sizes

Code:	BDPC8001
Size:	125ml
Barcode:	5060021369390

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties rights and, if necessary clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.



Certificate Number: 6152
ISO 9001
ISO 14001



BOND IT
Unit G16 River Bank Way, Lowfields Business Park,
Elland, West Yorkshire HX5 9DN.
Telephone: +44 (0)1422 315300 Fax +44 (0)1422 315310
Email: sales@bond-it.co.uk Website: www.bond-it.co.uk



V3 3/12/12